

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 152 027 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
07.11.2001 Bulletin 2001/45

(51) Int. Cl. **C08K 5/04, C09K 3/18,
C08L 23/02, C09D 5/02,
C08J 5/18, B65D 65/00,
A01G 9/14**

(21) Application number: **01810412.5**

(22) Date of filing: **26.04.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **04.05.2000 US 201871 P**

(71) Applicant: **Ciba Specialty Chemicals Holding Inc.
4057 Basel (CH)**

(72) Inventors:
• **Gupta, Anunay**
Holmdel, NJ 07733 (US)
• **Devore, David**
Nyack, NY 10960 (US)
• **McNamara, John James**
Putnam Valley, NY 10579 (US)
• **Zedda, Alessandro**
4057 Basel (CH)

(54) **Polyolefin film compositions with permanent antifog properties**

(57) Polyolefin films having incorporated therein a compound of the formula $\text{CH}_3\text{CH}_2(\text{CH}_2\text{CH}_2)_a\text{CH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_b\text{OH}$, where a is 9 to 25 and b is 1 to 10.

exhibit superior long lasting fog resistance. The polyolefin films are useful as packaging film for moist products and as a greenhouse film for agricultural applications.

EP 1 152 027 A1

Description

Polyolefin Film Compositions with Permanent Antifog Properties

[0001] This invention relates to novel olefin polymer compositions which are resistant to fogging, especially when employed as a packaging film for moist products and as a greenhouse film for agricultural applications.

Greenhouse film for agricultural applications

[0002] Agricultural films which are largely used in greenhouse culture or tunnel culture chiefly include soft ethylene resin films which are about 30 to 200 microns thick and which comprise, as a base resin, polyvinyl chloride (hereinafter abbreviated as PVC), branched low-density polyethylene (hereinafter abbreviated as LDPE), ethylene-vinyl acetate copolymers (hereinafter abbreviated as EVA), linear low-density polyethylene (hereinafter abbreviated as LLDPE), etc. Of the various properties required for the agricultural films, particularly important are weather resistance, anti-fogging properties, heat-retaining properties, and transparency. To cope with the recent situation confronting agriculture such as an increased cost and a shortage of labour, development of films having an extended duration of life before replacement is desired.

[0003] The atmosphere within greenhouses or tunnels surrounded by an agricultural film is saturated with water vapour which evaporates from the soil or plants, and the water vapour dropwise condenses on the inner surface of a cold film to cause fogging. Water droplets on the film not only greatly reduce the incident sunlight due to irregular reflection but the droplets fall on the plants resulting in frequent occurrence of diseases.

[0004] To avoid fogging, antifog treatments on the inner surface of an agricultural film converting the film into an anti-stick water film and preventing adhesion of water droplets have been used thereby assuring transmission of sunlight into the greenhouse or tunnel, raising the soil temperature and air temperature within the greenhouse or tunnel, accelerating photosynthesis of the plants, accelerating healthy growth of the plants, and controlling the occurrence of plant diseases.

[0005] Currently employed antifog treatments include incorporation of an anti-fogging agent (antifog additive) into a film-forming ethylene resin compound and coating of an anti-fogging agent on a film.

[0006] However, an anti-fogging film obtained by coating a soft plastic film with an anti-fogging agent has not yet been employed practically as an agricultural film for the following reasons. Because of their low surface energy, soft plastic films for agricultural use generally have poor wettability and adhesion when coated with surface active agents or hydrophilic high polymeric substances which have been used as anti-fogging agents. This tendency is particularly conspicuous with soft ethylene resin films of low polarity, e.g., LDPE, EVA, and LLDPE films. Therefore, where an anti-fogging agent is spray coated with a power atomiser onto a soft ethylene resin film, the anti-fogging agent needs to be used in a large quantity and this increases cost, and a large amount of time is required for spray coating operation. Further, spray coating cannot be effected uniformly with insufficient anti-fogging effects arising. Where an anti-fogging agent is applied using a coater, etc., a large quantity of a coating is consumed, and the coating speed cannot be increased, resulting in an increase of cost. In either case, the coated anti-fogging agent is washed away together with running water droplets due to poor adhesion resulting in a very short life for the anti-fogging properties. Furthermore, the coated film undergoes blocking due to the stickiness of the anti-fogging agent. As a result, it has been impossible to retain anti-fogging effects in a stable manner for a long duration of at least 1 year, more desirably, several years. Most of the state-of-the-art agricultural films exhibit anti-fogging properties for a period of only about 1 month.

[0007] Anti-fogging agents commonly incorporated into the films include non-ionic, anionic and cationic surface active agents.

[0008] Other methods for providing anti-fogging properties to agricultural films, in addition to the coating method and incorporation method, include chemical modification of the ethylene base resin or the ethylene resin film surface by introducing a polar group, such as a hydrophilic group. This technique, however, entails high cost at the present time and is difficult to apply to agricultural films.

[0009] On the other hand, coating type anti-fogging agents mainly comprising an inorganic hydrophilic colloidal substance and a hydrophilic organic compound have recently been developed as disclosed, e.g., in JP63-45432 and JP63-45717. Suitable inorganic hydrophilic colloidal substances include colloidal silica, colloidal alumina, colloidal Fe(OH)₂, colloidal Sn(OH)₄, colloidal TiO₂, colloidal BaSO₄, and colloidal lithium silicate, with colloidal silica and colloidal alumina most generally used. Suitable hydrophilic organic compounds include various non-ionic, anionic or cationic surface active agents; graft copolymers mainly comprising a hydroxyl-containing vinyl monomer unit and from 0.1 to 40% by weight of a carboxyl-containing vinyl monomer unit or a partial or complete neutralisation product thereof; and sulfo-containing polyester resins.

[0010] Coating type anti-fogging agents used with this new film type have markedly improved wettability and adhesion and coated agricultural films exhibiting anti-fogging properties for a duration of about a half year to about 1 year are

provided

[0011] Under these circumstances, none of the state-of-the-art polyolefin-based agricultural films satisfies the requirements of long lasting anti-fogging properties

5 Packaging film for moist products

[0012] In the field of packaging, whereby polymer films are used for covering or enclosing items of sale, and where film clarity or good optical properties are desired, there is a recognised need for polymer films which resist fogging when exposed to conditions of temperature and humidity which can produce condensation on the film. This condensation is especially troublesome when the interior of the package contains enough moisture to produce fogging of the interior surface of the film. Of special interest here is the packaging of food products, such as meats, bakery items, vegetables, fruits, and the like, though non-food items are also of interest.

[0013] Food products are often packaged in polymeric film for ease in handling by customers, to provide sanitary protection of the food product from the environment, to provide an easier and more economical wrapping than paper, or to provide a better view of the food product. Various polymeric materials such as polyvinyl chloride, poly(ethylene/vinyl acetate) and irradiated polyethylenes have been used in the food wrap market with plasticized polyvinyl chloride (PVC) being widely used in the market. Freshly cut meat and vegetables are often packaged in these films, and certain properties are desired of the film for it to perform satisfactorily as a food overwrap. Obviously, film used in this application should have good "see through" clarity so the product can be viewed. High gloss is desired to add "sparkle" to the packages for aesthetic appeal to the customers. As these food products are packaged, they generally experience a temperature change from where they are packaged to where they are stored or sold. This temperature change can cause the formation of water droplets on the inside surface of the film (commonly called "fog"). These water droplets are usually objectionable because they hinder the view of the food products from the consumer and can cause spoilage, particularly to certain vegetables. To prevent water from condensing in droplets, an antifog agent is often added to the film. The antifog agents reduce the surface tension of the water and cause the water to form a continuous sheet, which is then transparent.

[0014] There is a perceived need in the market place for improved packaging films, especially for food products, where the widely used plasticized polyvinylchloride (PVC) requires replacement by a more acceptable film. Much of the PVC which has been used is plasticized with additives, e.g. dioctyl phthalate, which are becoming less acceptable in the market.

[0015] U.S. Pat. No. 5,262,233 discloses agricultural films which may have incorporated therein an anti-fogging agent which may be a poly(ethylene oxide) of a long chain alcohol.

[0016] WO91/04853 describes a polymeric composition having enhanced surface energy comprising e.g. a compound of the formula $RO-(CH_2CH_2O)_nR$.

[0017] Atmer® 502, is described in a September, 1998 data sheet as having long-lasting antifog properties in LDPE agricultural film. Atmer® 502, an ethoxylated ether, is a trademark of ICI Americas.

[0018] The present invention pertains to polyolefin film compositions with anti-fogging properties comprising

(a) a polyolefin film; and

(b) a compound of the formula $CH_3CH_2(CH_2CH_2)_aCH_2CH_2(OCH_2CH_2)_bOH$

where a is 9 to 25 and b is 1 to 10.

[0019] In the compounds of the formula $CH_3CH_2(CH_2CH_2)_aCH_2CH_2(OCH_2CH_2)_bOH$ of component (b), the term "a" is for example 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24 or 25. The term "b" is for example 1, 2, 3, 4, 5, 6, 7, 8, 9 or 10.

[0020] Examples for polyolefins are:

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, poly-4-methylpent-1-ene, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), high density and high molecular weight polyethylene (HDPE HMW), high density and ultrahigh molecular weight polyethylene (HDPE-UHMW), medium density polyethylene (MDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), (VLDPE) and (ULDPE).

Polyolefins, i.e. the polymers of monoolefins exemplified in the preceding paragraph, preferably polyethylene and polypropylene, can be prepared by different, and especially by the following, methods:

(i) radical polymerisation (normally under high pressure and at elevated temperature)

ii) catalytic polymerisation using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either p- or s-coordinated. These metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used, typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, IIa and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler (-Natta), TNZ (DuPont), metallocene or single site catalysts (SSC).

2. Mixtures of the polymers mentioned under 1.), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).

3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene/propylene copolymers, linear low density polyethylene (LLDPE) and mixtures thereof with low density polyethylene (LDPE), propylene/but-1-ene copolymers, propylene/isobutylene copolymers, ethylene/but-1-ene copolymers, ethylene/hexene copolymers, ethylene/methylpentene copolymers, ethylene/heptene copolymers, ethylene/octene copolymers, propylene/butadiene copolymers, isobutylene/isoprene copolymers, ethylene/alkyl acrylate copolymers, ethylene/alkyl methacrylate copolymers, ethylene/vinyl acetate copolymers and their copolymers with carbon monoxide or ethylene/acrylic acid copolymers and their salts (ionomers) as well as terpolymers of ethylene with propylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene; and mixtures of such copolymers with one another and with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers, LDPE/ethylene-vinyl acetate copolymers (EVA), LDPE/ethylene-acrylic acid copolymers (EAA), LLDPE/EVA, LLDPE/EAA and alternating or random polyalkylene/carbon monoxide copolymers and mixtures thereof with other polymers, for example polyamides.

[0021] Preferred polyolefins are polyethylene or polypropylene and their copolymers with mono- and diolefins.


[0022] The ethylene polymers of the present invention are those that are characterised as having a melt index or melt flow value, in the range of about 0.01 to about 20 gms./10 min. as measured by ASTM-D-1238, condition E, and a density in the range of about 0.9 to about 0.96 gms./cc. This includes the branched polymers made at high pressure with a free-radical initiator and those made at low, medium, or high pressure using a co-ordination catalyst which gives the linear (i.e. substantially non-branched) polymers. Those made using a free-radical initiator (e.g. peroxy compounds) have become known in the art as "low density polyethylene" (LDPE) and those made using a co-ordination catalyst (e.g. a "Ziegler-type catalyst") have become known as "high density polyethylene" (HDPE).

[0023] More recently developed commercially are the so-called "linear low density polyethylenes" (LLDPE) which are prepared using a co-ordination catalyst, but which, because of the presence of minor amounts of co-polymerised higher olefins (especially olefins of 4-10 carbon atoms) have a density lower than HDPE, yet the arrangement of polymerised molecular units is of the linear type.

[0024] It is also contemplated within the purview of the present invention to employ ethylene polymers which contain other comonomers, such as acrylic acid, methacrylic acid, alkyl acrylates, vinyl esters, and carbon monoxide. These type of monomers, which contain oxygen atoms, are employed using a free-radical initiator, but are not very well suitable when co-ordination catalysts are employed. The co-ordination catalysts, which generally contain metal-carbon bonds, are usually poisoned or deactivated by compounds containing oxygen-carbon bonds or hydrogen-oxygen bonds when employed in quantities such as are involved in copolymerisation thereof. On the other hand, copolymerisation of ethylene with the higher hydrocarbon olefins is best done using a co-ordination type catalyst.

[0025] In the present invention, it is preferred that the ethylene polymer be of the LLDPE variety, especially those which have a melt flow value in the range of about 0.1-10 and enough comonomer units to give a density in the range of about 0.9 to about 0.935 g/cc, such comonomer units being an aliphatic hydrocarbon olefin of from 4 to 8 carbon atoms, including isomers in that range. These LLDPE polymers are recognised in the art as having excellent strength, resistance to tear propagation as shown by Dart Impact and Elmendorf Tear, and exhibit good resistance to tearing or puncturing when stressed against articles having protuberances. This preference for the LLDPE variety is especially important in food packaging applications and most especially in packaging of red meat.

[0026] The fog-resistant films of this invention are prepared by producing a film of a formulation comprising a polyolefin having incorporated therein an A-B diblock copolymer antifog agent. These copolymers are of the structure



where a is 9 to 25 and b is 1 to 10. Preferred are compositions comprising an A-B diblock compound where a is 13 and b is 2-5. The values for the indices a and b are average values.

[0027] The polymer formulations of the present invention preferably contain an amount of the antifog agent in the range of about 0.1% to about 4%, most preferably an amount in the range of about 0.5% to about 3%, based on the overall weight of the formulation.

[0028] The present compositions may comprise other known antifog additives, such as alkoxylated ethers, e.g. Atmer® 502, sorbitan esters, e.g. Atmer® 103, other known non-ionic, anionic and cationic surface active agents as disclosed in the foregoing U.S. Patents, e.g., polyoxyalkylene fatty acid esters, alkoxylated phenols, mixed mono-, di-, or triglycerides, fatty acid esters of polyhydroxy alcohols, other polyalkoxylated compounds and the like. Atmer® is a trademark of ICI Americas.

[0029] PCT application PCT/EP 01/00694, filed Jan. 23, 2001, incorporated herein by reference, discloses plastic films for food protection that comprise ultraviolet light absorbers. The present polyolefin films with fog resistance may also contain further appropriate additives such as ultraviolet light absorbers, hindered amine light stabilisers, antioxidants, processing aids and other additives as disclosed in PCT application PCT/EP 01/00694.

[0030] For example, the compositions of the invention may optionally also contain from about 0.01 to about 10%, preferably from about 0.025 to about 5%, and especially from about 0.1 to about 3% by weight of various conventional stabiliser coadditives, such as the materials listed below, or mixtures thereof.

1. Antioxidants

1.1 Alkylated monophenols, for example,

[0031]

- 2,6-di-tert-butyl-4-methylphenol
- 2-tert-butyl-4,6-dimethylphenol
- 2,6-di-tert-butyl-4-ethylphenol
- 2,6-di-tert-butyl-4-n-butylphenol
- 2,6-di-tert-butyl-4-i-butylphenol
- 2,6-di-cyclopentyl-4-methylphenol
- 2-(4-methylcyclohexyl)-4,6-dimethylphenol
- 2,6-di-octadecyl-4-methylphenol
- 2,4,6-tri-cyclohexylphenol
- 2,6-di-tert-butyl-4-methoxymethylphenol

1.2 Alkylated hydroquinones, for example,

[0032]

- 2,6-di-tert-butyl-4-methoxyphenol
- 2,5-di-tert-butyl-hydroquinone
- 2,5-di-tert-amyl-hydroquinone
- 2,6-diphenyl-4-octadecyloxyphenol

1.3 Hydroxylated thiodiphenyl ethers, for example

[0033]

- 2,2'-thio-bis-(6-tert-butyl-4-methylphenol)
- 2,2'-thio-bis-(4-cetylphenol)
- 4,4'-thio-bis-(6-tert-butyl-3-methylphenol)
- 4,4'-thio-bis-(6-tert-butyl-2-methylphenol)

1.4. Alkylidene-bisphenols. for example.

[0034]

- 5 2,2'-methylene-bis-(6-tert-butyl-4-methylphenol)
 2,2'-methylene-bis-(6-tert-butyl-4-ethylphenol)
 2,2'-methylene-bis-[4-methyl-6-(α -methylcyclohexyl)-phenol]
 2,2'-methylene-bis-(4-methyl-6-cyclohexylphenol)
 2,2'-methylene-bis-(6-nonyl-4-methylphenol)
 10 2,2'-methylene-bis-[6-(α -methylbenzyl)-4-nonylphenol]
 2,2'-methylene-bis-[6-(α,α -dimethylbenzyl)-4-nonylphenol]
 2,2'-methylene-bis-(4,6-di-tert-butylphenol)
 2,2'-ethylidene-bis-(4,6-di-tert-butylphenol)
 2,2'-ethylidene-bis-(6-tert-butyl-4-isobutylphenol)
 15 4,4'-methylene-bis-(2,6-di-tert-butylphenol)
 4,4'-methylene-bis-(6-tert-butyl-2-methylphenol)
 1,1-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-butane
 2,6-di-(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol
 1,1,3-tris-(5-tert-butyl-4-hydroxy-2-methylphenyl)-butane
 20 1,1-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane
 ethyleneglycol bis-[3,3-bis-(3'-tert-butyl-4'-hydroxyphenyl)-butyrate]
 di-(3-tert-butyl-4-hydroxy-5-methylphenyl)-dicyclopentadiene
 di-[2-(3'-tert-butyl-2'-hydroxy-5'-methyl-benzyl)-6-tert-butyl-4-methylphenyl] terephthalate.

25 1.5. Benzyl compounds. for example.

[0035]

- 1,3,5-tri-(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene
 30 di-(3,5-di-tert-butyl-4-hydroxybenzyl) sulphide
 3,5-di-tert-butyl-4-hydroxybenzyl-mercapto-acetic acid isooctyl ester
 bis-(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithiol terephthalate
 1,3,5-tris-(3,5-di-tert-butyl-4-hydroxybenzyl) isocyanurate
 1,3,5-tris-(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl) isocyanurate
 35 3,5-di-tert-butyl-4-hydroxybenzyl-phosphoric acid dioctadecyl ester
 3,5-di-tert-butyl-4-hydroxybenzyl-phosphoric acid monoethyl ester, calcium-salt

1.6. Acylaminophenols. for example.

40 [0036]

- 4-hydroxy-lauric acid anilide
 4-hydroxy-stearic acid anilide
 2,4-bis-octylmercapto-6-(3,5-tert-butyl-4-hydroxyanilino)-s-triazine
 45 octyl-N-(3,5-di-tert-butyl-4-hydroxyphenyl)-carbamate

1.7. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)-propionic acid with monohydric or polyhydric alcohols. for example.

[0037]

50

55

methanol	diethylene glycol
octadecanol	triethylene glycol
1,6-hexanediol	pentaerythritol
neopentyl glycol	tris-hydroxyethyl isocyanurate
thiodiethylene glycol	di-hydroxyethyl oxalic acid diamide
triethanolamine	triisopropanolamine

1.8. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)-propionic acid with monohydric or polyhydric alcohols for example

[0038]

methanol	d ethylene glycol
octadecanol	triethylene glycol
* 6-hexared ol	pentaerythritol
neopentyl glycol	tris-hydroxyethyl isocyanurate
thiodiethylene glycol	di-hydroxyethyl oxalic acid diamide
triethanolamine	triisopropanolamine

1.9. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)-propionic acid for example.

[0039]

N,N-di-(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexamethylenediamine
 N,N-di-(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-trimethylenediamine
 N,N-di-(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hydrazine

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)-benzotriazoles, for example, 2-(2-hydroxy-5-methylphenyl)-2H-benzotriazole, 2-(3,5-di-tert-butyl-2-hydroxyphenyl)-2H-benzotriazole, 2-(2-hydroxy-5-tert-butylphenyl)-2H-benzotriazole, 2-(2-hydroxy-5-tert-octylphenyl)-2H-benzotriazole, 5-chloro-2-(3,5-di-tert-butyl-2-hydroxyphenyl)-2H-benzotriazole, 5-chloro-2-(3-tert-butyl-2-hydroxy-5-methylphenyl)-2H-benzotriazole, 2-(3-sec-butyl-5-tert-butyl-2-hydroxyphenyl)-2H-benzotriazole, 2-(2-hydroxy-4-octyloxyphenyl)-2H-benzotriazole, 2-(3,5-di-tert-amyl-2-hydroxyphenyl)-2H-benzotriazole, 2-(3,5-bis- α -cumyl-2-hydroxyphenyl)-2H-benzotriazole, 2-(3-tert-butyl-2-hydroxy-5-(2-(ω -hydroxy-octyl)-ethyleneoxy)carbonyl-ethylphenyl)-2H-benzotriazole, 2-(3-dodecyl-2-hydroxy-5-methylphenyl)-2H-benzotriazole, 2-(3-tert-butyl-2-hydroxy-5-(2-octyloxy-carbonyl)ethylphenyl)-2H-benzotriazole, dodecylated 2-(2-hydroxy-5-methylphenyl)-2H-benzotriazole, 2-(3-tert-butyl-2-hydroxy-5-(2-octyloxy-carbonyl-ethyl)phenyl)-5-chloro-2H-benzotriazole, 2-(3-tert-butyl-5-(2-(2-ethylhexyloxy)-carbonyl-ethyl)-2-hydroxyphenyl)-5-chloro-2H-benzotriazole, 2-(3-tert-butyl-2-hydroxy-5-(2-methoxycarbonyl-ethyl)phenyl)-5-chloro-2H-benzotriazole, 2-(3-tert-butyl-2-hydroxy-5-(2-methoxycarbonyl-ethyl)phenyl)-2H-benzotriazole, 2-(3-tert-butyl-5-(2-(2-ethylhexyloxy)carbonyl-ethyl)-2-hydroxyphenyl)-2H-benzotriazole, 2-(3-tert-butyl-2-hydroxy-5-(2-isooctyloxy-carbonyl-ethyl)phenyl)-2H-benzotriazole, 2,2'-methylene-bis(4-tert-octyl-6-2H-benzotriazol-2-yl-phenol), 2-(2-hydroxy-3- α -cumyl-5-tert-octylphenyl)-2H-benzotriazole, 2-(2-hydroxy-3-tert-octyl-5- α -cumylphenyl)-2H-benzotriazole, 5-fluoro-2-(2-hydroxy-3,5-di- α -cumylphenyl)-2H-benzotriazole, 5-chloro-2-(2-hydroxy-3,5-di- α -cumylphenyl)-2H-benzotriazole, 5-chloro-2-(2-hydroxy-3- α -cumyl-5-tert-octylphenyl)-2H-benzotriazole, 2-(3-tert-butyl-2-hydroxy-5-(2-isooctyloxy-carbonyl-ethyl)phenyl)-5-chloro-2H-benzotriazole, 5-trifluoromethyl-2-(2-hydroxy-3- α -cumyl-5-tert-octylphenyl)-2H-benzotriazole, 5-trifluoromethyl-2-(2-hydroxy-5-tert-octylphenyl)-2H-benzotriazole, 5-trifluoromethyl-2-(2-hydroxy-3,5-di-tert-octylphenyl)-2H-benzotriazole, methyl 3-(5-trifluoromethyl-2H-benzotriazol-2-yl)-5-tert-butyl-4-hydroxyhydrocinnamate, 5-butylsulfonyl-2-(2-hydroxy-3- α -cumyl-5-tert-octylphenyl)-2H-benzotriazole, 5-trifluoromethyl-2-(2-hydroxy-3- α -cumyl-5-tert-butylphenyl)-2H-benzotriazole, 5-trifluoromethyl-2-(2-hydroxy-3,5-di- α -cumylphenyl)-2H-benzotriazole, 5-butylsulfonyl-2-(2-hydroxy-3,5-di-tert-butylphenyl)-2H-benzotriazole and 5-phenylsulfonyl-2-(2-hydroxy-3,5-di-tert-butylphenyl)-2H-benzotriazole

2.2. 2-Hydroxy-benzophenones, for example, the 4-hydroxy-, 4-methoxy-, 4-octyloxy-, 4-decyloxy-, 4-dodecyloxy-, 4-benzyloxy-, 4,2',4'-trihydroxy-, and 2'-hydroxy-4,4'-dimethoxy derivatives

2.3. Esters of optionally substituted benzoic acids for example, phenyl salicylate, 4-tert-butylphenyl salicylate, octylphenyl salicylate, dibenzoylresorcinol, bis-(4-tert-butylbenzoyl)-resorcinol, benzoylresorcinol, 3,5-di-tert-butyl-4-hydroxybenzoic acid, 2,4-di-tert-butylphenyl ester and 3,5-di-tert-butyl-4-hydroxybenzoic acid hexadecyl ester

2.4. Acrylates and malonates, for example, α -cyano- β -diphenylacrylic acid ethyl ester or isooctyl ester, α -

carbomethoxy-cinnamic acid methyl ester, α -cyano- β -methyl-p-methoxycinnamic acid methyl ester or butyl ester, α -carbomethoxy-p-methoxy-cinnamic acid methyl ester, N-(β -carbomethoxy- β -cyanovinyl)-2-methyl-in-doline, Sanduvor® PR25 and PR31.

2.5. Sterically hindered for example bis-(2,2,6,6-tetramethylpiperidyl) sebacate, bis-(1,2,2,6,6-pentamethylpiperidyl) sebacate, n-butyl-3,5-di-tert-butyl-4-hydroxybenzyl malonic acid bis-(1,2,2,6,6-pentanemethylpiperidyl)ester, condensation product of 1-hydroxyethyl-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, condensation product of N,N'-(2,2,6,6-tetramethylpiperidyl)-hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-s-triazine, tris-(2,2,6,6-tetramethylpiperidyl)-nitritotriacetate, tetrakis-(2,2,6,6-tetramethyl-4-piperidyl) 1,2,3,4-butanetetracarboxylate, 1,1'-(1,2-ethanediyl)-bis-(3,3,5,5-tetramethylpiperazinone), bis(1-octyloxy-2,2,6,6-tetramethylpiperidin-4-yl) sebacate

2.6. Sterically hindered amines substituted on the N-atom by a hydroxy-substituted alkoxy group, for example compounds disclosed in copending application Serial No. 09/257,711, and whose relevant parts are also incorporated herein by reference, such as 1-(2-hydroxy-2-methylpropoxy)-4-octadecanoyloxy-2,2,6,6-tetramethylpiperidine, 1-(2-hydroxy-2-methylpropoxy)-4-hydroxy-2,2,6,6-tetramethylpiperidine, 1-(2-hydroxy-2-methylpropoxy)-4-oxo-2,2,6,6-tetramethylpiperidine, bis(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethylpiperidin-4-yl) sebacate, bis(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethylpiperidin-4-yl) adipate, bis(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethylpiperidin-4-yl) succinate, bis(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethylpiperidin-4-yl) glutarate and 2,4-bis{N-[1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethylpiperidin-4-yl]-N-butylamino}-6-(2-hydroxyethylamino)-s-triazine.

2.7. Oxalic acid diamides, for example, 4,4'-di-octyloxy-oxanilide, 2,2'-di-octyloxy-5,5'-di-tert-butyl-oxanilide, 2,2'-di-dodecyloxy-5,5'-di-tert-butyl-oxanilide, 2-ethoxy-2'-ethyl-oxanilide, N,N'-bis(3-dimethylaminopropyl)-oxalamide, 2-ethoxy-5-tert-butyl-2'-ethyloxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butyloxanilide and mixtures of ortho- and paramethoxy- as well as of o- and p-ethoxy-disubstituted oxanilides.

2.8. Hydroxyphenyl-s-triazines, for example 4,6-bis-(2,4-dimethylphenyl)-2-(2-hydroxy-4-octyloxyphenyl)-s-triazine, Cyasorb® 1164, Cytec Corp., 4,6-bis-(2,4-dimethylphenyl)-2-(2,4-dihydroxyphenyl)-s-triazine, 2,4-bis(2,4-dihydroxyphenyl)-6-(4-chlorophenyl)-s-triazine, 2,4-bis[2-hydroxy-4-(2-hydroxyethoxy)phenyl]-6-(4-chlorophenyl)-s-triazine, 2,4-bis[2-hydroxy-4-(2-hydroxy-4-(2-hydroxyethoxy)phenyl)-6-(2,4-dimethylphenyl)-s-triazine, 2,4-bis[2-hydroxy-4-(2-hydroxyethoxy)phenyl]-6-(4-bromophenyl)-s-triazine, 2,4-bis[2-hydroxy-4-(2-acetoxyethoxy)phenyl]-6-(4-chlorophenyl)-s-triazine, 2,4-bis(2,4-dihydroxyphenyl)-6-(2,4-dimethylphenyl)-s-triazine, 2,4-bis(4-biphenyl)-6-(2-hydroxy-4-octyloxycarbonylethylideneoxyphenyl)-s-triazine, 2-phenyl-4-[2-hydroxy-4-(3-sec-butyloxy-2-hydroxypropyloxy)phenyl]-6-[2-hydroxy-4-(3-sec-amyloxy-2-hydroxypropyloxy)phenyl]-s-triazine, 2,4-bis(2,4-dimethylphenyl)-6-[2-hydroxy-4-(3-benzyloxy-2-hydroxypropyloxy)phenyl]-s-triazine, 2,4-bis(2-hydroxy-4-n-butyloxyphenyl)-6-(2,4-di-n-butyloxyphenyl)-s-triazine, 2,4-bis(2,4-dimethylphenyl)-6-[2-hydroxy-4-(3-nonyloxy*2-hydroxypropyloxy)-5- α -cumylphenyl]-s-triazine (* denotes a mixture of octyloxy, nonyloxy and decyloxy groups)methylenebis-{2,4-bis(2,4-dimethylphenyl)-6-[2-hydroxy-4-(3-butyloxy-2-hydroxypropoxy)phenyl]-s-triazine}, methylene bridged dimer mixture bridged in the 3:5', 5:5' and 3:3' positions in a 5:4:1 ratio, 2,4,6-tris(2-hydroxy-4-isooctyloxycarbonylisopropylideneoxyphenyl)-s-triazine, 2,4-bis(2,4-dimethylphenyl)-6-(2-hydroxy-4-hexyloxy-5- α -cumylphenyl)-s-triazine, 2-(2,4,6-trimethylphenyl)-4,6-bis[2-hydroxy-4-(3-butyloxy-2-hydroxypropyloxy)phenyl]-s-triazine, 2,4,6-tris[2-hydroxy-4-(3-sec-butyloxy-2-hydroxypropyloxy)phenyl]-s-triazine, mixture of 4,6-bis-(2,4-dimethylphenyl)-2-(2-hydroxy-4-(3-dodecyloxy-2-hydroxypropoxy)-phenyl)-s-triazine and 4,6-bis-(2,4-dimethylphenyl)-2-(2-hydroxy-4-(3-tridecyloxy-2-hydroxypropoxy)-phenyl)-s-triazine, Tinuvin® 400, Ciba Specialty Chemicals Corp., 4,6-bis-(2,4-dimethylphenyl)-2-(2-hydroxy-4-(3-(2-ethylhexyloxy)-2-hydroxypropoxy)-phenyl)-s-triazine and 4,6-diphenyl-2-(4-hexyloxy-2-hydroxyphenyl)-s-triazine.

3. Phosphites and phosphonites, for example, triphenyl phosphite, diphenylalkyl phosphites, phenyldialkyl phosphites, tri(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, di-stearyl-pentaerythritol diphosphite, tri-(2,4-di-tert-butylphenyl) phosphite, diisododecylpentaerythritol diphosphite, di-(2,4,6-tri-tert-butylphenyl)-pentaerythritol diphosphite, di-(2,4-di-tert-butyl-6-methylphenyl)-pentaerythritol diphosphite, di-(2,4-di-tert-butylphenyl)pentaerythritol diphosphite, tristearyl-sorbitol triphosphite, tetrakis-(2,4-di-tert-butylphenyl) 4,4'-diphenylenediphosphonite.

4. Compounds which destroy peroxide, for example, esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercapto-benzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyl-dithi-

ccarbamate dioctadecyl disulfide pentaerythritol tetrakis-(3-dodecylmercapto)-propionate

5 5. Hydroxylamines for example N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-diocetylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine

10 6. Nitrones for example, N-benzyl-alpha-phenyl nitron, N-ethyl-alpha-methyl nitron, N-octyl-alpha-heptyl nitron, N-lauryl-alpha-undecyl nitron, N-tetradecyl-alpha-tridecyl nitron, N-hexadecyl-alpha-pentadecyl nitron, N-octadecyl-alpha-heptadecyl nitron, N-hexadecyl-alpha-heptadecyl nitron, N-octadecyl-alpha-pentadecyl nitron, N-heptadecyl-alpha-heptadecyl nitron, N-octadecyl-alpha-hexadecyl nitron, nitron derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine

15 7. Amine oxides for example amine oxide derivatives as disclosed in U.S. Patent Nos. 5,844,029 and 5,880,191, oidecyl methyl amine oxide, tridecyl amine oxide, tridecyl amine oxide and trihexadecyl amine oxide

8. Polyamide stabilizers for example copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese

20 9. Basic co-stabilizers for example, melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids for example Ca stearate, Zn stearate, Mg stearate, Na ricinoleate and K palmitate, antimony pyrocatecholate or zinc pyrocatecholate.

25 10. Nucleating agents for example, inorganic substances such as talcum, metal oxides such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulphates of, preferably, alkaline earth metals; organic compounds such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds such as ionic copolymers (ionomers)

30 11. Fillers and reinforcing agents for example, calcium carbonate, silicates, glass fibers, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite.

35 12. Other additives for example, plasticizers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow-control agents, optical brighteners, clarifiers such as substituted and unsubstituted bisbenzylidene sorbitols, flameproofing agents, anti-static agents, blowing agents and thiosynergists such as dilauryl thiodipropionate or distearyl thiodipropionate

40 13. Benzofuranones and indolinones for example those disclosed in US4325863, US4338244 or US5175312, or 3-[4-(2-acetoxyethoxy)phenyl]-5,7-di-tert-butyl-benzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)-benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butyl-benzofuran-2-one

45 14. Nickel compounds for example nickel complexes of 2,2'-thio-bis-[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel diisobutyldithiocarbamate, nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenylundecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands

55 **[0040]** The mixing of the antifog agents into the polyolefin is done by mixing it into molten polymer by commonly used techniques such as roll-milling, mixing in a Banbury type mixer, or mixing in an extruder barrel and the like. The heat history (time at which held at elevated temperature) can be shortened by mixing the antifog agent with unheated polymer particles so as to achieve substantially even distribution of the agent in the mass of polymer, thereby reducing the amount of time needed for intensive mixing at molten temperature.

[0041] Conveniently, the antifog agent can also be added substantially simultaneously or sequentially with any other additives (colorants, tackifiers, slip agents, block agents, and the like) which may be desired in certain instances. The

antifog agents may also be preblended with other additives and the blend then added to the polymer. It is contemplated that in some instances these antifog agents should have the additional benefit of aiding the other additives to become more easily or evenly dispersed or dissolved in the polyolefin. For easier batch-to-batch control of quality, it may be preferred to employ concentrated masterbatches of polymer/agent blends which are subsequently blended, as portions, to additional quantities of polymer to achieve the final desired formulation. The masterbatch, or the neat additives, may be injected into freshly prepared polymer while the polymer is still molten and after it leaves the polymerisation vessel or train, and blended therewith before the molten polymer is chilled to a solid or taken to further processing. It is within the purview of the present invention to employ blends or alloys of olefin polymers, whether they be of the above described LDPE, LLDPE, HDPE or other olefin polymers or copolymers made using a free-radical initiator or a co-ordination catalyst. Polypropylene is an example of an olefin polymer made using a co-ordination catalyst (e.g. the well-known Ziegler or Natta catalysts or variations thereof) yet which inherently exhibits a low density compared to polyethylene.

[0042] It is well known in the art that polybutene or polyisobutylene is an effective tackifier or cling agent when mixed in polyethylene. In packaging processes, good cling properties are desirable in instances wherein the film is expected to cling to itself until pulled apart or until heat-sealed, as the case may be. The polybutenes or polyisobutylenes usually employed for this purpose are generally used in small quantities of only a few percentage points of the total and are usually of low or relatively low molecular weight, having weight average mol weights in the range of from several hundred to a few thousand. The use of such tackifiers is preferred in certain of the formulations contemplated as being within the purview of the present invention, especially in meat packaging (and the like) where it is desired that substantially no liquid leaks occur during the packaging operation until heat-sealed, or during shipping, storage, and handling after being heat-sealed.

[0043] The making of films of polyolefins is well-known and includes the techniques of casting films as thin sheets through narrow slit dies, and the blown-film technique wherein an extruded tube of molten polymer is inflated to the desired "bubble" diameter and/or film thickness before being cooled and collected or further processed. These present formulations are also suitable in coextrusion fabrication of films wherein two or more films comprise a multi-layer structure. The antifog agents of the present invention can exude through an adjacent film layer which does not contain the antifog agent, thereby rendering the adjacent layer resistant to fogging.

[0044] In one preferred aspect, the invention comprises a composition of a polyolefin resin and additives to form a film suitable for a red meat overwrap. Polyolefin resins have the needed strength, optical, and gas permeability properties required for this market. However, they lack the wettability required to prevent moisture droplet formation in the package at lower temperatures. To solve the wettability problem, anti-fogging agents (such as mono- and diglycerides) commonly used in plasticized PVC film were tried in polyolefin resins. These additives were not as effective in polyolefin resins as they were in plasticized PVC film. The lack of plasticizers in polyolefin films might contribute to the difference observed in anti-fogging agents' behaviour. Anti-fogging agents must be able to exude to the surface of the film where they can be effective, but not be abraded from the surface of the film. Anti-fogging agents that can be easily removed by water or by abrasion from the surface of the film are not desirable because the anti-fogging agents could flavour the meat, and the film would not be fog resistant. Thus, the invention comprises the unique composition of an polyolefin resin and an effective anti-fogging agent that is not easily abraded from the surface of the film. The use for this mixture of polyolefin resin and anti-fogging agent can be in food overwrap (meat, vegetables, etc.), greenhouse film, or other applications where a clear film with wettability or non-fogging is needed.

[0045] This invention differs from the widely used PVC red meat overwrap and produce wrap in that the base resin is a polyolefin instead of polyvinyl chloride resin. Polyolefin resin has the advantage of not requiring plasticizers (e.g. dioctyl phthalate) such as required and used in PVC films. Antifog agents perform differently in the two different classes of resin. Due to the plasticizers in PVC film, antifog agents are not as easily washed off the surface of the film. Thus, not all antifog agents that work in plasticized PVC film will work in polyolefin resin films.

[0046] Also, the present invention incorporates the anti-fogging agent within the resin instead of applying it as a coating. The incorporation of the additive into the resin is less expensive, less labour intensive, and more consistent than coatings applied to the surface of the film. Thus, the present invention utilises anti-fogging agents that maintain their anti-fogging ability on the surface of the film even when the film has experienced abrasion. This aspect is important during the wrapping of food products so as to prevent the food products from absorbing the anti-fogging agent and to maintain the wettability of the film in the package.

[0047] Furthermore, the present invention allows the antifog agents to be incorporated into the resin, and the resin made into film by standard techniques with no additional treatment needed. No irradiation or heat ageing is necessary to cause the antifog agent to exude to the surface of the film where it is then effective. The antifog agents exude to the surface of the film within approximately 48 hours after fabrication.

[0048] The polyolefin films of this invention with antifog properties are advantageously used for greenhouse films and for films used for food packaging applications.

[0049] The following examples are to illustrate some particular embodiments, but the present invention is not limited

to the particular ones illustrated

Example 1

[0050] In order to evaluate the antifogging properties of the claimed compounds in LDPE films, they are incorporated in the polymer according the following procedure. Appropriate amounts of each compound are weighed and added to LDPE pellets (Riblene FF 29 supplied by Polimeri Europa, Milan, Italy), characterized by a density of 0.921 g/cm³ and a melt flow index (190°C 2.15 Kg) of 0.61, in order to obtain formulations containing 1, 1.5 or 2% by weight of each compound. The granules so obtained are blown in a semi-industrial Dolci blow-extruder at a maximum temperature of 210°C to give films 150µm thick.

Anti-fogging Test Method

[0051] Films are evaluated according to the hot fog test: A 250 mL glass beaker, containing about 50 mL of water and covered with the film to be evaluated, is immersed to about ¾ of its height in a water bath at 60°C. Films are observed at defined intervals from the start of the experiment and a conventional notation ranging from A to E is assigned. Results are in Table 1.

Rating for Hot fog Tests:			
Description	Performance	Rating	Comments
An opaque layer of small fog droplets	None	A	Zero visibility poor light transmission
An opaque layer of large droplets	None	B	Zero visibility poor light transmission
A complete layer of large dripping transparent droplets	Poor	C	Poor visibility, lens effect.
Randomly scattered large transparent droplets	Fair	D	Discontinuous film of water
Few small or large transparent droplets	Good	D/E	Disc. film of water, mostly transparent
A transparent film displaying no visible water	Excellent	E	Completely transparent

Table 1

Additive	MW	a	b	Hrs at D/E Hot fog test
none	---	---	---	(constant B/C rating)
1% Atmer® 103	430	---	---	500
1% 98-02*8	575	13	2.5	650
1% 98-02*6	875	23	4	1100
1.5% Atmer® 502	344	7	2	350
1.5% 98-0218	575	13	2.5	1950
2% Atmer® 103	430	---	---	750
2% 98-02*8	575	13	2.5	2400
2% 98-02*6	875	23	4	1500

[0052] Additives are of the formula $\text{CH}_3\text{CH}_2(\text{CH}_2\text{CH}_2)_a\text{CH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_b\text{OH}$ and the indices a and b are average values and refer to this formula

[0053] A high number of hours at antifog rating of D/E is desired. It is seen that antifog additives of the present invention provide superior long lasting results.

Example 2

[0054] Example 1 is repeated to obtain formulations containing 1 or 2% by weight of the additives of Table 2. Films of about 75µm are obtained.

[0055] Films are evaluated according the hot fog test as described in Example 1. Results are found in the table below.

Table 2

Additive	MW	a	b	Hrs at D/E Hot fog test
1% Atmer® 103	430	--	---	175
1% 98-0218	575	13	2.5	1100
1% 98-0216	875	23	4	350
1% 98-0222	920	13	10.5	150
1% 98-0224	1100	18	12.5	50
2% Atmer® 103	430	---	--	200
2% 98-0218	575	13	2.5	1200

[0056] Additives are of the formula $\text{CH}_3\text{CH}_2(\text{CH}_2\text{CH}_2)_a\text{CH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_b\text{OH}$, and the indices a and b are average values and refer to this formula.

[0057] A high number of hours at antifog rating of D/E is desired. It is seen that antifog additives of the present invention provide superior long lasting results.

Claims

1. A fog-resistant polyolefin film composition comprising

(a) a polyolefin film, and

(b) a compound of the formula $\text{CH}_3\text{CH}_2(\text{CH}_2\text{CH}_2)_a\text{CH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_b\text{OH}$ where a is 9 to 25 and b is 1 to 10.

2. A composition according to claim 1 in which the polyolefin is polyethylene.

3. A composition according to claim 1 in which component (b) is a compound of the formula $\text{CH}_3\text{CH}_2(\text{CH}_2\text{CH}_2)_{13}\text{CH}_2\text{CH}_2(\text{OCH}_2\text{CH}_2)_{2.5}\text{OH}$.

4. A composition according to claim 1 in which the polyolefin film is a greenhouse film.

5. A composition according to claim 1 in which the polyolefin film is a food packaging film.

6. The use of a composition according to claim 1 as red meat overwrap.



European Patent
Office

EUROPEAN

REPORT

Application Number
EP C1 81 0412

DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document with indication, where appropriate of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (InCL1.7)
X	EP 0 869 146 A (MITSUI CHEMICALS INC) 7 October 1998 (1998-10-07) * claims 1,3,17,23 * * page 15, line 7-10 * * page 6, line 10,11 * * page 27, line 2-7 * ---	1,2,4,5	C08K5/04 C09K3/18 C08L23/02 C09D5/02 C08J5/18 B65D65/00 A01G9/14
X	US 5 766 772 A (BAX SERGE ET AL) 16 June 1998 (1998-06-16) * claims 1,7,16 * ---	1,2,5,6	
X	US 3 048 266 A (UNION CARBIDE CORPORATION) 7 August 1962 (1962-08-07) * claims 1,9 * * examples 21,22 * ---	1,2,5,6	
D,X	EP 0 500 073 A (MITSUBISHI PETROCHEMICAL CO) 26 August 1992 (1992-08-26) * claims 1,5 * ---	1,2,4	
P,X	EP 1 055 610 A (MITSUI CHEMICALS INC MITSUI KAGAKU PLATECH CO LTD (JP)) 29 November 2000 (2000-11-29) * claims 1,11 * * page 4, line 32 * ---	1,5	TECHNICAL FIELDS SEARCHED (InCL1.7) C08K C09D C09K C08J B65D A01G
A	EP 0 492 463 A (SUMITOMO CHEMICAL CO) 1 July 1992 (1992-07-01) * claims 1,12 * -----	1-6	

The present search report has been drawn up for all claims

Place of search	Date of completion of the search	Examiner
THE HAGUE	26 July 2001	Rose, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background U: non-written disclosure P: intermediate document</p> <p>I: theory or principle underlying the invention E: earlier patent document, but published on or after the filing date C: document cited in the application D: document cited for other reasons A: member of the same patent family as corresponding document</p>		

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 81 0412

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

26-07-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0869146 A	07-10-1998	CA 2240012 A	30-04-1998
		CN 1212003 A	24-03-1999
		WO 9817721 A	30-04-1998
US 5766772 A	16-06-1998	IT 1269174 B	21-03-1997
		AT 198078 T	15-12-2000
		AU 690216 B	23-04-1998
		AU 1678195 A	01-08-1995
		CA 2208028 A	13-07-1995
		DE 69519628 D	18-01-2001
		DE 69519628 T	03-05-2001
		DK 739398 T	02-01-2001
		EP 0739398 A	30-10-1996
		ES 2153470 T	01-03-2001
		NZ 279603 A	24-11-1997
		PT 739398 T	30-04-2001
		WO 9518845 A	13-07-1995
US 3048266 A	07-08-1962	BE 615683 A	
		DE 1494382 A	12-03-1970
		GB 941796 A	13-11-1963
EP 0500073 A	26-08-1992	JP 4264140 A	18-09-1992
		JP 3043865 B	22-05-2000
		JP 5112725 A	07-05-1993
		JP 3071904 B	31-07-2000
		JP 5124161 A	21-05-1993
		DE 69219635 D	19-06-1997
		DE 69219635 T	23-10-1997
		ES 2104745 T	16-10-1997
		US 5262233 A	16-11-1993
EP 1055610 A	29-11-2000	CN 1283652 A	14-02-2001
		JP 2001040116 A	13-02-2001
EP 0492463 A	01-07-1992	JP 2903713 B	14-06-1999
		JP 4220444 A	11-08-1992
		JP 4220445 A	11-08-1992
		JP 2560547 B	04-12-1996
		JP 4220446 A	11-08-1992
		BR 9105552 A	01-09-1992
		CA 2058110 A	22-06-1992
		DE 69113421 D	02-11-1995
		DE 69113421 T	11-04-1996
		US 5346944 A	13-09-1994

EPO FORM P/04.8

For more details about this annex see Official Journal of the European Patent Office, No. 12/82